



TECHNICAL DATA SHEET

INTERFACE PLUS 42.38

Artikl: A5500

Description : Flock lined nitrile gloves

Features & * Nitrile rubber for solvent resistance

Benefits : * Outstanding abrasion resistance

* Anti-slip pattern for good grip in wet and dry conditions

* Straight cuff

* Ingredients comply with FDA regulations for food contact

* Extra long length for added protection

* Manufactured under a stringent quality management system

Applications : Industrial Cleaning, Petrochemical Industry, Aerospace and Automobile Industry, Printing Industry, Surface Coating, Metal Fabrication

Product Details :

Elastomer : Nitrile rubber

Thickness : 0.42 mm +/- 0.05

Lining : Flocklined

Former : Reverse Lozenge, CIVL

Cuff type : Straight

Exterior : Matt finish

Colours : Green G8

CE Certification : Conforms to European Council Directive 89/686/EEC relating to (Complex Design) Personal Protective Equipment after assessment against standards EN 374, EN 388 & EN 420:2003



Chemical Risks
EN 374



Mechanical Risks
EN 388



Micro O. Risks
EN 374

| Chemical Risks | Mechanical Risks | Micro O. Risks |
|---|------------------|------------------------------|
| Methanol | Level 3 | Abrasion resistance Level 4 |
| n-Heptane | Level 6 | Blade cut resistance Level 1 |
| Sodium hydroxide, 40% | Level 6 | Tear resistance Level 0 |
| Sulphuric acid, 95-98% | Level 4 | Puncture resistance Level 1 |
| Acetic acid, glacial | Level 3 | |
| Acetonitrile | Level 1 | |
| Ammonium hydroxide (33% NH ₃) | Level 5 | |
| Amyl acetate | Level 3 | |
| Amyl alcohol | Level 6 | |
| Butanol | Level 6 | |
| Butyl acetate | Level 2 | |
| Butyl cellosolve (CAS 111-76-2) | Level 6 | |
| Carbon disulphide | Level 1 | |
| Chlorine gas | Level 6 | |
| Cyclohexane | Level 6 | |
| Cyclohexanol | Level 6 | |
| Di-isobutyl ketone | Level 5 | |
| Diethylene glycol | Level 6 | |
| Dimethyl acetamide (CAS 127-19-5) | Level 1 | |
| Dimethyl sulphoxide | Level 2 | |
| Ethanol, 95% | Level 5 | |
| 2-Ethoxy ethanol | Level 4 | |
| 2-Ethoxy ethyl acetate | Level 3 | |
| Ethyl acetate | Level 1 | |
| Ethylene glycol | Level 6 | |
| Ethyl ether | Level 2 | |
| Formaldehyde, 37% | Level 6 | |
| Hexane | Level 6 | |
| Hydrazene monohydrate (64-65% H ₂ H ₄) (CAS 7803-57-8) | Level 6 | |
| Hydrochloric acid, 37% | Level 6 | |
| Hydrofluoric acid, 40% | Level 4 | |
| Hydrogen peroxide 30% (CAS 7722-84-1) | Level 6 | |
| Isopropanol | Level 6 | |
| Iso octane | Level 6 | |
| Kerosene | Level 6 | |
| Lactic acid, 85% | Level 6 | |
| Maleic acid (saturated) | Level 6 | |
| Methyl methacrylate | Level 1 | |
| Methyl propyl ketone | Level 1 | |
| Methyl tert-butyl ether | Level 5 | |
| Naphtha solvent | Level 5 | |
| Nitric acid, 40% | Level 6 | |
| Octyl alcohol | Level 6 | |
| Orthophosphoric acid, 85% | Level 6 | |
| Perchloric acid | Level 6 | |
| Petroleum ether (CAS 8032-32-4) | Level 6 | |
| Petrol unleaded | Level 6 | |
| Potassium hydroxide, 50% | Level 6 | |
| Propyl acetate | Level 1 | |
| Sodium hydroxide, 50% | Level 6 | |
| Sodium hypochlorite, 10-15% | Level 6 | |



| | |
|-------------------------------|---------|
| 1,1,2,2-tetrachloroethane | Level 1 |
| Tetrachloroethylene | Level 5 |
| 1,1,1-trichloroethane | Level 1 |
| Turpentine | Level 6 |
| White spirit (CAS 8052-41-3) | Level 6 |
| White spirit (CAS 64742-48-9) | Level 6 |
| White spirit (CAS 68551-17-7) | Level 6 |
| Xylene (mixture of isomers) | Level 2 |

Conforms to : ASTM D4679 of 2002

| Physical Dimensions : | Size | Palm | Wrist | Cuff | Length |
|-----------------------|-------|------|-------|------|--------|
| | 6 1/2 | 199 | 212 | 274 | 380 |
| | 7 1/2 | 213 | 226 | 282 | 380 |
| | 8 1/2 | 227 | 241 | 286 | 380 |
| | 9 | 228 | 245 | 293 | 380 |
| | 10 | 247 | 261 | 308 | 380 |

Circumference in mm,+/- 5 mm Tolerance +/- 10 mm